



Chemical & Metallurgical Services

(NABL ACCREDITED LABORATORY)



T.S.No.63-A, SIDCO Industrial Estate, Ekkaduthangal, Chennai - 600 032, Tamilnadu INDIA.
 Phone : 91-44-2225 3863, Tele Fax : 91-44-2225 2944, Mobile : 9445067918
 After Off. Hrs : 91-44-2245 1794 E-mail : cmslab81@gmail.com / rmdnayar@gmail.com

TEST CERTIFICATE

Page: 1 of 1

Test Report No.	: CMS/LTR/T-11115-Y/2016-17	Date	: 13-03-2017
Issued To	: M/s.Ramco Industrial Limited "Auras Corporate Centre" II & VI Floor 98A, Dr. Radhakrishnan Road, Post Box No. 2949, Mylapore, Ch-4.		
Your Ref.	: Letter Dt: 05.02.2017,		
No. of Samples	: 1No.	Date of Receipt of Sample	: 06-03-2017
Nature of Test	: Physical Test	Date of Testing	: 10-03-2017
Enclosures	: Nil		

TEST RESULTS

Test Method : IS: 14862, ASTM D-1032, IS: 2380, ASTM C1185.

Sample Details

Fibre Cement Board (HICEM FLEXO)

TEST	RESULT
1) Modulus of Rupture	
(a) Parallel to fibre	= 14.7 N/mm ²
(b) Perpendicular to fibre	= 8.6 N/mm ²
2) Compressive Strength	= 31.5 N/mm ²
3) Tensile Strength	
(a) Parallel to fibre	= 21.2 N/mm ²
(b) Perpendicular to fibre	= 18.3 N/mm ²
4) Screw withdrawal strength	= 1850 N
5) Moisture content EMC	= 11 %
6) Water Absorption	= 36 %
7) Density	= 1250
8) Dry Wet Shrinkage	= 0.19 %
9) Water Impermeability	= No deposit of water at the bottom after 24 hours

Remarks:- Passes the test

R.M.D. NAYAR
(Ex- Scientist - NML - CSIR)
Technical Director

****END****

Recognised & Approved Laboratory by Steel Authority of India Ltd, RITES LTD, Airports Authority of INDIA LTD, Defence Establishments, National & International Third Party Inspection Agencies & Many other State & Central Government Establishments.

Note:- This report relates only to the particular Sample submitted for test. Any correction not attested shall invalidate this certificate. Sample will be destroyed after 15 days from the date of issue of certificate unless instructed otherwise. Any complaints about this report should be communicated in writing within 7 days of the issue of this report. This report should not be reproduced wholly or in parts and cannot be used as evidence in a court of law and shall not be used in advertising media without prior permission in writing. Sample descriptions is not verified in all case and is given as described by the customers. Samples are not drawn by us unless otherwise stated.